



## POLYETHYLENE BLOWN GRADES



NAME OF GRADE	MFI	Density (g/cm <sup>3</sup> )	Application
<b>HDPE-BL3</b>	23 (190°C/21.6 kg)	0.954	<ul style="list-style-type: none"> <li>- Small blow moulding</li> <li>- Containers (up to 5 lit )</li> <li>- Packaging of pharmaceuticals &amp; surfactants</li> </ul>
<b>HDPE-0035</b>	0.35 (190°C/2.16 kg)	0.959	<ul style="list-style-type: none"> <li>- Bottles for bleach</li> <li>- Motor oil</li> <li>- Toiletries</li> <li>- Mild and distilled water</li> <li>- To make small containers</li> </ul>
<b>LDPE-2420D</b>	0.25 (190°C/2.16kg)	0.923	<ul style="list-style-type: none"> <li>- Shrink Film</li> <li>- Bottles for Consumer Goods</li> <li>- Bags &amp; Pouches</li> <li>- Blown Film</li> </ul>
<b>LDPE-0075</b>	0.75 (190°C/2.16kg)	0.92	<ul style="list-style-type: none"> <li>- carrier bags</li> <li>- industrial film</li> <li>- blow moulding of small containers</li> <li>- packaging of pharmaceutical products</li> <li>- packaging of foodstuffs</li> <li>- large bottles</li> <li>- dust bin liners</li> <li>- shrink film</li> </ul>

